

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	COL1784347
Name:	Mississippi Rebels Blue
Type:	Polyester

Powder Properties

Specific Gravity	Approx. 1.57 g/cm ³
Storage Temp	Less than 80°F (27°C)
Theoretical Coverage	139 sq. ft/lb. @ 1 mil
Particle Distribution	n/a

Coating Properties

Film Thickness	Recommended film thickness: 2.5 - 3.5 mils
Cure Schedule	Metal Temperature: 10 minutes @ 392°F (200°C)
Gloss Level	85% - 100% @ 60°
Pencil Hardness	H - 2H (ASTM D3363)
Flexibility	n/a
Adhesion	5B
Direct Impact	80 in-lb. direct;
Reverse Impact	80 in-lb. reverse (ASTM D2794)
Salt Spray	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

www.columbiacoatings.com