

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



Number:	X55200054
Name:	Super Texture White
Type:	Polyester

Powder Properties

Specific Gravity	1.63 (\pm 0.05) g/cm ³
Storage Temp	< 80°F (27°C) up to 1 year
Theoretical Coverage	59 ft ² /lb. @ 2 mils
Particle Distribution	25 – 50 microns

Coating Properties

Film Thickness	Recommended Film Thickness: 2 – 3 mils
Cure Schedule	Metal Temperature: 10 minutes @ 400°F (204°C)
Gloss Level	50% – 60% @ 60°
Pencil Hardness	H – 2H (ASTM D3363)
Flexibility	1/8" (ASTM D522) (Conical Mandrel)
Adhesion	4B (ASTM D3359)
Direct Impact	120 in/lb. (ASTM D2794)
Reverse Impact	120 in/lb. (ASTM D2794)
Salt Spray	1000 hrs. (ASTM B117)

www.columbiacoatings.com