

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



COLUMBIA
COATINGS

Number:	X5351039
Name:	Aged Bronze Vein
Type:	Polyester

Powder Properties

Specific Gravity	1.55 ± .05 g/cm ³
Storage Temp	Maximum 80°F (27°C)
Theoretical Coverage	124 sq./ft @ 1 mil
Particle Distribution	25 - 50 MICRONS AVERAGE

Coating Properties

Film Thickness	2.5 - 3.5 mils
Cure Schedule	Metal Temperature: 10 minutes @ 400°F (204°C)
Gloss Level	40% - 55% @ 60°
Pencil Hardness	H-2H
Flexibility	100%
Adhesion	4B
Direct Impact	160 inch/pounds- Pass
Reverse Impact	160 inch/pounds- Pass
Salt Spray	1000 hrs.

www.columbiacoatings.com