

Columbia Coatings

Technical Data Sheet

Columbia Coatings
1173 Industrial Park Rd
Columbia, TN 38401
931-388-7730
931-388-5573 FAX



COLUMBIA
COATINGS

Number:	F20930024
Name:	Snowblind
Type:	Polyester

Powder Properties

Specific Gravity	1.71
Storage Temp	80°F (27°C) up to 1 year
Theoretical Coverage	56.49 SQ. FT./LB. @ 2 MILS
Particle Distribution	25 - 50 MICRONS AVERAGE

Coating Properties

Film Thickness	Recommended Film Thickness: 2 – 4 mils
Cure Schedule	Metal Temperature: 10 minutes @ 400°F (204°C)
Gloss Level	10% +/-7%
Pencil Hardness	2H
Flexibility	100%
Adhesion	4B
Direct Impact	80 in-lb. direct;
Reverse Impact	80 in-lb. reverse (ASTM D2794)
Salt Spray	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

www.columbiacoatings.com